

P O L Y M E R ABSTRACTS OF J A P A N

(11)Publication number : 06-019136

(43)Date of publication of application : 28.01.1994

(51)Int.Cl.

G03F 7/038

G03F 7/039

H01L 21/027

(21)Application number : 04-196572

(71)Applicant : NIPPON OIL CO LTD

(22)Date of filing : 30.06.1992

(72)Inventor : AOKI NOBUO

(54) PHOTSENSITIVE MATERIAL

(57)Abstract:

PURPOSE: To provide a resist which satisfies the requirement for high resolution and high sensitivity by adding photosensitive group to Fullerene.

CONSTITUTION: Photosensitive groups are added to Fullerene which is a carbon allotrope called as a carbon cluster. Fullerene expressed by molecular formula C60 or C70 is preferably used. Any functional groups which can cause chemical reaction by irradiation of UV rays, for UV rays, X-rays, electron beams or the like can be used as the photosensitive groups. To introduce photosensitive groups to Fullerene, normal chemical reaction is used. For example, Fullerene is stirred in alkyl amine at room temp. for several hours to add alkyl amino to the Fullerene and then the reaction with methacryl chloride is effected at room temp. for several hours. Thus, a photosensitive material having methacrylamide group as photosensitive groups can be synthesized. This photosensitive material has high dry etching resistance and can be used in a thin film state, so that the film has high resolution and high sensitivity.

LEGAL STATUS

[Date of request for examination] 10.11.1997

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 2814165

[Date of registration] 14.08.1998

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right] 14.08.2003

Copyright (C); 1998,2003 Japan Patent Office